

revive™ 100 Media Matt



Technical, Print & Environmental Specifications

Spec / Gsm	Unit	57	60	65	70	80	90
Bulk	ISO534 cm3/g	1.11	1.15	1.15	1.14	1.06	1.11
Caliper	um	63.0	69.00	75.0	80.0	85	100
Gloss (Hunter)	% ISO8254-1	18.0	18.0	18.0	18.0	18.0	18.0
Brightness	% ISO2470	82.0	82.0	84.0	84.0	84.0	84.0
Opacity	DIN53146	>92	>92	>92	>92	>94	>94

* Please note that these grammages are only available direct from the mill - please check with your local sales office for minimum order quantities and leadtimes.

Print Suitability

- Offset Litho
- HSWO
- Litho
- Gravure

Finishing

- Advertising Materials
- Magazines
- Brochures
- Manuals
- Inserts

Printing inks suitable for uncoated paper should be used.

Denmaur always recommend trial sheets on new presses to assess suitability.

Environmental Accreditations and Certifications



for further information, please contact your local sales office

Issue 2.0 - 13th March 2017



