

revive™ 100 Media Silk



Technical, Print & Environmental Specifications

Spec / Gsm	Unit	54	57	60	65	70	80	90
Bulk	ISO534 cm3/g	0.95	0.95	0.95	0.95	0.95	0.95	0.95
Caliper	um	51.3	54.2	57.0	61.8	66.5	76.0	85.5
Gloss (Hunter)	% ISO8254-1	35.0	35.0	35.0	35.0	40.0	40.0	40.0
Brightness	% ISO2470	80.0	82.0	82.0	84.0	84.0	84.0	84.0
Opacity	DIN53146	>92	>92	>92	>92	>92	>94	>94

Print Suitability

- Offset Litho
- HSWO
- Litho
- Gravure

Typical End Uses

- Advertising Materials
- Magazines
- Brochures
- Manuals
- Inserts

Printing inks suitable for uncoated paper should be used.

Denmaur always recommend trial sheets on new presses to assess suitability.

Environmental Accreditations and Certifications



for further information, please contact your local sales office

Issue 2.0 - 13th March 2017



