



revive™ 100 Natural Offset

Technical, Print & Environmental Specifications

Revive 100 Natural Offset					
GSM	Thickness mic	Bulk cm ³ /g	Whiteness CIE	Opacity %	Bendtsen nl/min
70	81	1.15	90	91	25
80	103	1.29	90	93	45
90	116	1.29	90	95	45
100	134	1.34	90	96	25
115	156	1.36	90	97	25
135	175	1.30	90	98	25
150	188	1.25	90	98	25
170	212	1.25	90	98	25
190	238	1.25	90	98	20
250	288	1.15	90	98	20
300	345	1.15	90	98	20

Print Suitability

- Offset Litho
- Letterpress
- Silkscreen

Finishing

- Varnishing
- Die Cutting
- Foil Blocking
- Embossing
- Folding

Environmental Accreditations and Certifications



Availability: Please note this range is stocked at the mill.