



revive™ 100 Offset

Technical, Print & Environmental Specifications

Revive 100 Offset					
GSM	Thickness mic	Bulk cm ³ /g	Whiteness CIE	Opacity %	Bendtsen nl/min
80	100	1.25	150	92	120
90	113	1.25	150	93	120
100	125	1.25	150	94	120
120	150	1.25	150	95	120
140	175	1.25	150	97	120
150	188	1.25	150	98	150
170	213	1.25	150	98	180
190	237	1.25	150	98	200
250	288	1.15	150	98	120
300	345	1.15	150	98	150
350	403	1.15	150	98	180

Print Suitability

- Offset Litho
- Letterpress
- Silkscreen
- HSWO

Finishing

- Varnishing
- Film Lamination
- Foil Blocking
- Embossing
- Folding
- Die Cutting

Environmental Accreditations and Certifications

