



revive™ 100 Silk

Technical, Print & Environmental Specifications

Revive 100 Silk					
GSM	Thickness mic	Bulk cm ³ /g	Brightness %	Opacity %	Whiteness CIE
100	77	0.77	96	94	120
115	88	0.77	96	95	120
130	100	0.77	96	96	120
150	115	0.77	96	97	120
170	134	0.79	96	98	121
200	162	0.81	96	98	121
250	207	0.83	96	98	121
300	261	0.87	96	98	121
350	315	0.90	96	98	121

Print Suitability

- Offset Litho
- Letterpress
- Silkscreen
- HSWO

Finishing

- Varnishing
- Film Lamination
- Foil Blocking
- Embossing
- Folding
- Die Cutting

Environmental Accreditations and Certifications

