



revive™ 50 Offset

Technical, Print & Environmental Specifications

Revive 50 Offset					
GSM	Thickness mic	Bulk cm ³ /g	Whiteness CIE	Opacity %	Bendtsen nl/min
80	100	1.25	150	92	150
90	113	1.26	150	93	150
100	125	1.25	150	94	150
110	138	1.25	150	96	150
135	169	1.25	150	97	150
150	188	1.25	150	98	180
170	213	1.25	150	98	180
250	312	1.25	150	98	250
300	375	1.25	150	98	250

Print Suitability

- Offset Litho
- Letterpress
- Silkscreen

Finishing

- Varnishing
- Die Cutting
- Foil Blocking
- Embossing
- Folding

Availability: Please note this range is stocked at the mill.

Environmental Accreditations and Certifications

