



revive™ 50 Silk

Technical, Print & Environmental Specifications

Revive 50 Silk					
GSM	Thickness mic	Bulk cm ³ /g	Brightness %	Opacity %	Smoothness Bekk S
90*	73	0.81	97	92.5	500
100*	80	0.80	97	94	500
115	92	0.80	97	95	500
130	104	0.80	97	96	450
150	120	0.80	97	97	400
170	136	0.80	97	98	350
200*	165	0.83	97	98	300
250*	215	0.86	97	98	200
300*	270	0.90	97	98	150
350*	325	0.93	97	98	100

Print Suitability

- Offset Litho
- Letterpress
- Silkscreen
- HSWO

Finishing

- Varnishing
- Film Lamination
- Foil Blocking
- Embossing
- Folding
- Die Cutting

Environmental Accreditations and Certifications



*Please note that these weights are stocked at the mill.